

KLEIBERIT 701.4

Reactive PUR Hotmelt adhesive

Fields of use

- Highly stressed membrane, leather and textile laminating
- Laminating foam to textile material

Advantages

- For universal application, suitable for all application systems
- Low melting temperature
- Long open time
- Fluorescent - enables application quality to be checked
- Activation is possible using infra-red or hot air

Properties of the bond

- Very high bond strength following cross-linking
- Excellent heat and cold resistance
- Soft textile grip
- Wash resistant
- Resistant to chemical dry cleaning
- Very favourable fogging characteristics

Properties of the adhesive

Base: Polyurethane

Specific gravity: approx. 1.1 g/cm³

Viscosity (on the day of manufacture)

- Brookfield HBTD 10 rpm:

at 80 °C: approx. 8,000 ± 2,000 mPa·s

at 100 °C: approx. 4,000 ± 1,500 mPa·s

at 120 °C: approx. 2,500 ± 500 mPa·s

Identification: Identification is required according to EU regulations, contains Diphenylmethan-4,4'-diisocyanate (See our safety data sheet)

Hotmelt adhesives give off vapours even if the prescribed working temperature has been observed, and as a result unpleasant odours can develop. If the prescribed working temperature is considerably exceeded over a prolonged period, harmful decomposition products can also develop. Precautions should be taken to eliminate vapours, e.g. by using a suitable extraction ventilation system.

Processing

KLEIBERIT 701.4 is supplied in tightly closed containers suitable for use in melting plants. The hotmelt application aggregate should be designed to protect the adhesive from direct exposure to humidity.

Special attention must be paid to precise temperature control of the whole plant (record start data of the machine).

The adhesive is applied with rollers (engraving roller), nozzles (spray application), screen, etc. The application temperature is dependant upon the type of substrate and is normally within the range of 80° C - 100° C.

Chemical cross linking of PUR hotmelts requires moisture. Therefore sufficient air humidity has to be present during processing.

Subsequent cross-linking of the adhesive film follows during the course of 1-3 days, according to the moisture level.

Final strength will be reached after approx. 10 days.

Tests of the service properties of the bond, e.g. washing, chemical dry cleaning, etc. should only be performed following thorough cross-linking of the adhesive (i.e., after approx. 10 days).

Application devices

- Cartridge hand gun for manual application
- Bulk melters for 20 and 200 litre drums

Cleaning

Immediately following work, run the application plant until dry, or drain off the remaining adhesive. Immediately insert EVA Hotmelt Cleaning Compound - KLEIBERIT 761.2, melt and apply until all traces of PUR Hotmelt have been removed. Cured (dried) Hotmelt adhesive can only be removed mechanically.

KLEIBERIT 701.4

Packaging

KLEIBERIT 701.4:

carton with 12 cartridges at 0.3 kg net each
metal bucket, at 20 kg net each
metal drum, 180 kg net

Cleaning Compound

KLEIBERIT 761.2:

metal drum, 190 kg net

Additional packaging size available upon request.

Storage

KLEIBERIT 701.4 can be stored in factory sealed containers for approx. 12 months

Protect from humidity!

Version 18/02/25 ga; replaces previous versions

Disposal of containers and contents

Waste disposal key 080409
080410 – Adhesive fully cured

Disposal of contents and/or containers should comply with all applicable federal, state and local regulations.
Our containers are made of recyclable material.

Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.