

KLEIBERIT 701.7.30

Reactive PUR Hotmelt Adhesives

Fields of use

- Highly stressed membrane, leather and textile laminating
- Laminating foam to textile material

Advantages

- Adhesive with very high green strength, therefore shorter production times for multilayer compounds
- Very good wetting
- Fluorescent - enables application quality to be checked
- Activation is possible using infra-red or hot air
- Fast curing
- Free of harmful substances, tested and certified in accordance with OEKO-TEX® (valid ECO passport ZHXA 101889)



Properties of the bond

- Very high bond strength following cross-linking
- Extremely good resistance to heat and cold
- Soft textile grip
- Resistant to washing
- Resistant to chemical dry cleaning
- Very favourable fogging characteristics
- KLEIBERIT 701.7.30 tested in accordance with BS EN ISO 105-X18 „Phenolic yellowing“ and BS EN ISO G02 :1997 „Color Fastness to burnt gas fumes“

Properties of the adhesive

Base: Polyurethane
Density: approx. 1.05 g/cm³

Viscosity (on the day of manufacture)

- Brookfield HBTD 10 rpm:

at 100 °C: 9,000 ± 2,000 mPa·s
 at 120 °C: 3,000 ± 500 mPa·s

Identification: See our safety data sheet

Hotmelt adhesives give off vapours even if the prescribed working temperature has been observed, and as a result unpleasant odours can develop. If the prescribed working temperature is considerably exceeded over a prolonged period, harmful decomposition products can also develop. Precautions should be taken to eliminate vapours, e.g. by using a suitable extraction ventilation system.

Processing

KLEIBERIT 701.7.30 is supplied in tightly closed containers suitable for use in melting plants. The hotmelt application aggregate should be designed to protect the adhesive from direct exposure to humidity.

Special attention must be paid to precise temperature control of the whole plant (record start data of the machine).

The adhesive is applied with rollers (engraving roller), nozzles (spray application), screen, etc. The application temperature is dependant upon the type of substrate and is normally within the range of 100 – 140 °C.

Chemical cross linking of PUR hotmelts requires moisture. Therefore sufficient air humidity has to be present during processing.

Subsequent cross-linking of the adhesive film follows during the course of 1-3 days, according to the moisture level

Final strength will be reached after approx. 10 days.

Tests of the service properties of the bond, e.g. washing, chemical dry cleaning, etc. should only be performed following thorough cross-linking of the adhesive (i.e., after approx. 10 days).

Application devices

- Cartridge hand gun for manual application
- Melting tanks with nitrogen protection blanket
- Bulk melters for 20 and 200 litre drums

KLEIBERIT 701.7.30

Cleaning

Immediately following work with KLEIBERIT 701.7.30, run the application plant until dry, or drain off the remaining adhesive. Immediately insert EVA Hotmelt Cleaning Compound - KLEIBERIT 761.2 for a screen print plant, insert KLEIBERIT 761.8 for a melt print plant, melt and apply until all traces of PUR Hotmelt have been removed. Cured (dried) hotmelt adhesive can only be removed mechanically.

Packaging

KLEIBERIT 701.7.30:

aluminum bag in fiber drum, 20 kg net
drum, 200 kg net

Cleaning Compound

KLEIBERIT 761.2:

bag, 2 kg net
metal pail, 15 kg net

Cleaning Compound

KLEIBERIT 761.8:

plastic pail, 20 kg net
fibre drum, 136 kg net

Additional packaging sizes available upon request.

Storage

KLEIBERIT 701.7.30 can be stored in factory sealed containers for approx. 12 months.

Protect from humidity!

Version 22.05.2025 al; replaces previous versions

Disposal of containers and contents

Waste disposal key 080409

080410 – Adhesive fully cured

Disposal of contents and/or containers should comply with all applicable federal, state and local regulations.
Our containers are made of recyclable material.

Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.