

# KLEIBERIT 304.3

## Special Hardener

### Fields of application

- Spray with a duo-pistol together with KLEIBERIT 410 (different colours)
- As accelerator to reduce the aerating time together with KLEIBERIT 416.3

### Properties of KLEIBERIT 304.3

**Base:** aqueous salt solution

**Specific weight:** approx. 1.3 g/cm<sup>3</sup>

**ph-value:** approx. 1

**Viscosity**

**(4 mm DIN cup):** approx. 12 seconds

**Colour:** transparent, yellow

**Identification:** identification required according to EU regulations.  
(See our safety data sheet)

## Application

KLEIBERIT 410 or KLEIBERIT 416.3 and KLEIBERIT 304.3 are processed together by means of a special duo pistol.

The hardener is sprayed directly into the spray cone of the adhesive through a separate nozzle on the pistol.

Spraying ratio KLEIBERIT 410 / 304.3  
= 100 : 5 to 15 weight %.

Spraying ratio KLEIBERIT 416.3 / 304.3  
= 100 : 5 to 10 weight %.

With this method there is no pot life.

## Packaging

plastic canisters, 28 kg net

Additional packaging sizes upon request

## Storage

KLEIBERIT 304.3 can be stored in factory-sealed containers for approximately 1 year.

Protect from frosting!

Version 20/05/2019 xv

## KLEIBERIT 304.3

### Activator and Waste Disposal

#### Waste Code 060314

Our containers are made of recyclable material. Well drained containers can be recycled.

### Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.