

KLEIBERIT 706.0.37

Reactive PUR-Hotmelt Adhesive

Fields of application

- Good adhesion to various materials, such as polystyrene, wood, plaster, woven material, wood material, PVC, aluminium and metal plate (dependant upon the material used, pre-treatment could be necessary)
- Suitable for the production of household sponges

Advantages

- Following cross-linking, a highly heat resistant, watertight, extremely cold resistant and highly durable bond is attained
- Low processing temperature
- Long open time

Properties of the adhesive

Base: polyurethane
Specific weight: approx. 1.1 g/cm³
Viscosity (on the day of production)
Brookfield HBTD 10 rpm:
 at 120 °C 12,000 ± 3,000 mPa s
 at 140 °C 6,000 ± 1,500 mPa s

Identification: identification required according to EU regulations; contains diphenylmethane-4,4'-diisocyanate, (see our safety data sheet)

Attention

When hotmelt adhesives are melted and applied, vapours are set free and an unpleasant odour can occur, even if the recommended working temperature has been observed. Moreover if the prescribed working temperature is exceeded over a longer period, harmful decomposition products can develop. Precautions should be taken to eliminate the vapours, e.g. by using a suitable ventilation system.

Application techniques

For spray lamination, KLEIBERIT 706.0.37 is processed with melting equipment (suitable for PUR hotmelt adhesives) on a spray or roller coater application unit.

Climatise substrate to room temperature before processing. The following parameters are the minimum requirements for processing:

Room climate: from 20 °C/40% RH
 Substrate temp: from 20 °C
 Adhesive application temp: 120 – 130 °C
 Adhesive application quantity: from 40 g/m²

Open time under named conditions:
 ca. 30 seconds

In general, the optimal conditions for the respective applications must be determined on-site by the user with preliminary testing, documentation and continuous control.

Chemical cross linking of PUR hotmelts requires moisture. Therefore sufficient air humidity has to be present during processing.

Application devices

- Tank device with a nitrogen blanket
- Barrel melting plant for 20 litre containers
- Suitable roller application systems

Cleaning

Following completion of the work with KLEIBERIT 706.0.37, either run the application empty or drain off the remaining contents. Immediately afterwards apply melted Cleaning Agent KLEIBERIT 761.8 and reverse the direction of the rollers until the last traces of PUR hotmelt have been removed. Hotmelt adhesive which has already cross-linked can only be removed mechanically.

KLEIBERIT 706.0.37

Packaging

KLEIBERIT 706.0.37:

pouch pack, 20 kg net
metal drum, 190 kg net

Cleaning Agent

KLEIBERIT 761.8:

plastic pail, 20 kg net
fibre drum, 136 kg net

Additional packaging sizes available upon request.

Storage

KLEIBERIT 706.0.37 can be stored in factory
sealed containers for 12 months.

Protect from humidity!

Version 30/08/2019 xv

Waste Disposal

Disposal of contents and/or containers should comply with all applicable federal, state and local regulations.
Our containers are made of recyclable material.

Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.