

# KLEIBERIT 706.2.50 -ME-

**Reactive hotmelt based on polyurethane (PUR) for surface lamination**

## Fields of application

- Surface lamination
- Good adhesion to various materials, such as wood, wood material and PVC (dependant upon the material used, pre-treatment could be necessary)

## Advantages

- Following cross-linking, a heat resistant, watertight and extremely cold resistant bond is attained
- Very high green strength

## Properties of the adhesive

<b>Base:</b>	polyurethane
<b>Specific weight:</b>	approx. 1.1 g/cm <sup>3</sup>
<b>Viscosity</b> (on the day of production)	
<b>Brookfield HBTD 10 rpm:</b>	
at 120° C:	12,000 ± 3,000 mPa s
at 140° C:	6,000 ± 2,000 mPa s

**Identification:** Identification not required according to the German hazardous substances regulations GefStoffV.

**-ME product (Micro-Emission)**  
**Residual monomer content < 0.1%**

## Attention

When hotmelt adhesives are melted and applied, vapours are set free and an unpleasant odour can occur, even if the recommended working temperature has been observed. Moreover if the prescribed working temperature is exceeded over a longer period, harmful decomposition products can develop. Precautions should be taken to eliminate the vapours, e.g. by using a suitable ventilation system.

## Application techniques

For surface lamination, KLEIBERIT 706.2.50 ME is processed with melting equipment (suitable for PUR hotmelt adhesives) on a roller coater application unit.

Climatise substrate to room temp. before processing. The following parameters are the minimum requirements for processing:

Room climate: from 20°C/40% RH  
 Substrate temp: from 20°C  
 Adhesive application temp: 120 – 130°C  
 Adhesive application qty:  
 from 80 g/m<sup>2</sup> for laminate  
 from 50 g/m<sup>2</sup> for foils

Open time under named conditions: up to 6minutes

In general, the optimal conditions for the respective applications must be determined on-site by the user with preliminary testing, documentation and continuous control.

Chemical cross linking of PUR hotmelts requires moisture. Therefore sufficient air humidity has to be present during processing.

## Application devices

- Tank device with a nitrogen blanket
- Barrel melting plant for 20 and 200 litre containers
- Suitable roller application systems

## Cleaning

Following completion of the work with KLEIBERIT 706.2.50 ME, either run the application empty or drain off the remaining contents. Immediately afterwards apply melted KLEIBERIT Cleaning Agent 761.8 and reverse the direction of the rollers until the last traces of PUR hotmelt have been removed. Hotmelt adhesive which has already cross-linked can only be removed mechanically.

## KLEIBERIT 706.2.50 -ME-

### Packaging

#### KLEIBERIT 706.2.50 ME:

Carton with 4 pouch packs at 1.8 kg net each

Metal drum, 190 kg net

#### KLEIBERIT Cleaning Agent 761.8:

Fibre drum, 136 kg net

Plastic pail, 20 kg net

Additional packaging sizes available upon request.

### Storage

KLEIBERIT 706.2.50 ME can be stored in factory sealed containers for approx. 12 months.

Protect from humidity!

Version 29/07/2021 lz; replaces previous version

#### Adhesives and Waste Disposal

##### Waste Code 080409

080410 - Adhesive fully cured

Our containers are made of recyclable material. Well drained containers can be recycled.

#### Service

Our application department may be consulted at any time without obligation. The statements made herein are based on our experience gained to date. They are to be considered as information without obligation. Please test and establish for yourself the suitability of our products for your particular purposes. No liability exceeding the value of our product can be derived from the foregoing statements. This also applies to the technical consultancy service which is rendered free of charge and without obligation.